



TYPE	A	B	C	D	E
TO-126	Ø6.10 ±0.1	Ø3.00 ±0.05	Ø2.50 ±0.05	Ø2.90 ±0.05	Ø1.10 ±0.1

Insulating TO-220 Nylon Bushing Physical Property Data Sheet			
Property	Test Method (ASTM)	Unit	
Density	D-782	g/cm	1,5
24hours Water Aborption Rate	D-570	%	0,6
Hardness	D-785	R-scale	121
Flexural Strength	D-790	Pai	32000
Flexural Modulus	D-790	Psi	1200000
Tensile Strength	D-638	Psi	23000
Elongation	D-638	%	2
Mold Shrinkage	D-955	%	0,3
Heat Distortion Temperature	D-848		280
Combustion Characteristic	UL94		V-0